

ABSTRACT OF THE DISCLOSURE

Difference in retardation between two points separated by 1 cm along the TD direction of a polyvinyl alcohol polymer film 6 is 5 nm or less. The length of a surface for drying a polyvinyl alcohol polymer film 6 is 3 m to 200 m, and the water content of the polyvinyl alcohol polymer film 6 when peeled after passing through the drying surface is 50% by weight or less, in film formation.

UNITED STATES PATENT AND TRADEMARK OFFICE
DOCUMENT CLASSIFICATION BARCODE SHEET



Drawings

7

Level - 2
Version 1.1




Fig. 1